



## DESCRIPTION

Fiberfrax Duraboard products are manufactured from Fiberfrax refractory ceramic fibres, blended with specially selected inorganic and organic binders to give rigid boards with exceptional characteristics. Duraboard 120ZK is easy to cut and shape with standard tools. These boards exhibit high strength and rigidity coupled with excellent insulating performance and high temperature stability. Duraboard 120LD is particularly suited to applications where reduced out-gassing and/or high definition mechanical machining are required. Fiberfrax Duraboard products are available in a wide range of sizes and thicknesses.

## GENERAL CHARACTERISTICS

Fiberfrax Duraboard products have the following outstanding characteristics:

- High temperature stability
- Low thermal conductivity
- Resistance to thermal shock
- Resistance to erosion
- Easy to cut with standard tools

## TYPICAL APPLICATIONS

- High temperature furnace and kiln linings
- Rigid high temperature gaskets and seals
- Heat shields
- Gas boiler combustion chamber linings

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*Start saving energy now.  
Contact your local distributor.*

**Unifrax Ltd.**

T:+44 (0)1744 88 7600

F:+44 (0) 1744 88 9916

[www.unifrax.com](http://www.unifrax.com)

## TYPICAL PRODUCT PARAMETERS

Duraboard	120ZK	120LD
<b>Typical Chemical Analysis (fibre wt.%)</b>		
SiO <sub>2</sub>	50.0 - 58.0	50.0 - 58.0
Al <sub>2</sub> O <sub>3</sub>	42.0 - 50.0	42.0 - 50.0
Fe <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub>	<0.2	<0.2
Alkalis	<0.25	<0.25
<b>Physical Properties</b>		
Colour	White / Tan	White / Tan
Melting point (°C)	1760	1760
Product Density (kg/m <sup>3</sup> )	390	300
Modulus of Rupture (kPa)	>800	>700
Use Limit (°C) *	1200	1200
Loss on ignition (wt.%)	<9.0	<7.0
<b>Thermal Conductivity (W/mK)</b>		
<b>Mean Temp.</b>		
600 °C	0.13	0.09
800 °C	0.16	0.13
1000 °C	0.19	0.17
<b>Permanent Linear Shrinkage (%) 24 Hour Soak</b>		
1200 °C	<4.0	<4.0

\*Use limit refers to the maximum short term temperature limit. The maximum continuous use limit for boards depends upon application conditions. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

## AVAILABILITY

Thickness (mm)	120ZK	120LD	Sheets per carton	Sheets per pallet	Sheets per carton	Sheets per pallet
	Sheet Dimensions		1000 x 610mm	1250 x 1000mm		
3	✓		32	704	32	352
5	✓	✓	20	440	20	220
6	✓	✓	16	352	16	176
10	✓	✓	10	220	10	110
12	✓	✓	8	176	8	88
15	✓	✓	6	132	6	66
18	✓	✓	5	110	5	55
20	✓	✓	5	110	5	55
25	✓	✓	4	88	4	44
30	✓	✓	3	68	3	34
40	✓	✓	2	44	2	22
50	✓	✓	2	44	2	22
60		✓	1	32	1	16
75		✓	1	22	1	11

Other thicknesses / sizes may be available on request subject to minimum order requirements.

## HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.